

For applications requiring more detailed technical data, please contact our specialists.

Properties	Testing Method	Unit	Values	Values
<b>Mechanical</b>				
Apparent density*	DIN 53 479	g/cm <sup>2</sup>	0.5	0.7
Tensile strength	DIN 53 455	N/mm <sup>2</sup>	12	20
Elongation at tear	DIN 53 455	%	15	15
Flexural strength	DIN 53 452	N/mm <sup>2</sup>	20	30
Compressive strength (range of elasticity)	DIN 53 421 (serving as a basis)	N/mm <sup>2</sup>	>3.0	>3.0
Compressive stress at 30%	DIN 53 421 (serving as a basis)	N/mm <sup>2</sup>	>6.5	>13
Modulus of elasticity	DIN 53 457 (similar to)	N/mm	850	1100
Impact strength	DIN 53 453	kJ/m <sup>2</sup>	20	15
Shore hardness D	DIN 53 505		48	55
<b>Thermal</b>				
Vicat softening temp.	DIN 53 460	°C	78	75
Vicat A Temp of deflection under load acc. To ISO 75 (HDT)	DIN 53 461	°C	68	60
Coefficient of linear thermal expansion $\alpha$ (-30°C to +50°C)	DIN 53 752	mm/m °C	0.08	0.08
Thermal conductivity (0°C to +60°C)	DIN 53 616	W/mK	0.06	0.10
Thermal Resistance R — 0.5" thick	C518		.948	
Thermal Resistance R per Inch — 0.5" thick	C518		2.17	
<b>Electrical</b>				
Surface resistance	DIN VDE 0303 T3	$\Omega$	$6 \cdot 10^{14}$	$>1 \cdot 10$
Volume resistivity	DIN VDE 0303 T3	$\Omega \times \text{cm}$	$>10^{16}$	$4 \cdot 10^{15}$
Dielectric constant $E_d$	DIN VDE 0303 T2	kV/mm	5.0	16
Dielectric constant $E_r$ (at 1 kHz)	DIN 53 483 T2		$1.6 \pm 0.5$	2.5
Dielectric dissipation factor $\tan \delta$ (at kHz)	DIN 53 483 T2		0.012	0.016
Comparative figure of tracking	DIN IEC 112		CTI 600	CTI 600

For applications requiring more detailed technical data, please contact our specialists.

Properties	Testing Method	Unit	Values	Values
<b>Other</b>				
Water absorption after 7 days	DIN 53 495	%	<0.3	<0.3
Fire behavior	DIN 4102 (D)	1 - 6 mm		B1
	UL 94 (USA)	≥ 2 mm		VO
	NFP 92-501 (F)	2 - 6 mm		M1
		(3 - 6 mm colored)		
	VKF (CH)	2 - 6 mm		V.3
	VKF (CH)	10 mm	V.3	
	Italy (I)	2 - 6 mm		Class 1
Flame Spread Index				
Komatex — White	E84-03	45		
Komatex — Black	E84-03	10		
Komatex — Color	E84-03	15		
Smoke Developed Index				
Komatex — White	E84-03		850	
Komatex — Black	E84-03		400	
Komatex — Color	E84-03		350	
Allowable for contact with foodstuff				Yes

\*These are standard values that apply to an average density. Small variations depending on the sheet thickness are possible. Technical specifications are subject to change.